

GeoRock®

Geotextile Sand Container Datasheet:

0.75M³ CONTAINER STANDARD GRADE

DESCRIPTION

GeoRock® Geotextile Sand Containers are made of very robust staple fibre geotextile layers sewn together with a UV Stable polyester/polypropylene yarn.

GEOTEXTILE FEATURES

- High tensile strength
- High penetration resistance
- High permeability
- Excellent fines retention
- Abrasion resistant staple fibre construction
- High UV resistance

GEOTEXTILE PROPERTIES

Staple fibre geotextile

PROPERTIES		UNITS	VALUE	TEST METHOD
Mass		g/m ²	800	AS3706.1
Tensile Strength (Toughness)	Machine Direction	kJ/m ²	15	AS3706.2
	Cross Direction	kJ/m ²	20	
Puncture Resistance	CBR	kN	10	AS3706.4
	Drop Cone	mm	0	EN ISO 13433
Abrasion Resistance	BAW Rotating Drum	kN/m	30	BAW Abrasion Test

SEWING CONNECTION PROPERTIES

The sewing utilizes a straight lock chain stitch and overlock stitch using UV stabilized polymer yarns.

Seam Strength	Machine Direction	kN/m	39	AS3706.6
	Cross Direction	kN/m	49	

UV RESISTANCE

Retained Tensile Strength after UV Exposure	After 500 Hours	kN/m	25	ASTM D4355
	After 1000 Hours	kN/m	19	
	After 2000 Hours	kN/m	18	

FILLED PROPERTIES

The Geotextile Sand Containers once filled with sand and ready for placement with suitable equipment will have the following characteristics

Typical Fill	1.6m Long x 1.2m Wide x 0.4m Deep
Typical Filled Mass	Approximately 1300kg based on filling with sand of density 1650kg/m ³

SCOUR /ANCHOR FLAP OPTION

Scour/Anchor Flap	An additional geotextile flap can be integrally connected to the container to assist in preventing under scour of sand filled geotextile container structures
-------------------	---

* All values are MARV (Minimum Average Roll Values) based on testing over long periods of time. The right is reserved to make changes without notice at any time.

DISTRIBUTORS OF :

Geotextiles
Geogrids
Dewatering Tubes
Subsoil Drainage
Wick Drains
Erosion Control
Gabions & Rock Mattresses
Industrial Fabrics
Lining Systems



IMPORTANT NOTICE

The information provided in this document is general in content and offered in good faith. The content does not consider site specific locality and conditions. Data and specifications contained in this guideline are values obtained from laboratory testing. The right is reserved to make changes without notice at any time. Please consult your regional Global Synthetic representative to confirm current specification values. If you have any doubts as to the installation instructions or the application on your site, please contact us for clarification before commencing installation. It is recommended that advice be obtained from a qualified consulting engineer for your design and application requirements.

APRIL 18



Global Synthetics
 Australian Company – Global Expertise

SYDNEY

P: (02) 9725 4321

F: (02) 9725 4304

E: info@globalsynthetics.com.au | www.globalsynthetics.com.au

BRISBANE

P: (07) 3865 7000

F: (07) 3865 4444

PERTH

P: (08) 9459 4300

F: (08) 9459 4311

MELBOURNE

P: (03) 9791 1772

F: (03) 9791 1776

ADELAIDE

P: (08) 8384 8894

F: (08) 8384 3886